



Product Data

Castrol Tribol® 800 Range

Synthetic Gear Oils

DESCRIPTION

Castrol Tribol 800 synthetic gear oils have been developed for the lubrication of heavily loaded gears, bushings and bearings which may operate over a broad range of temperatures from ambient to elevated temperatures (>80°C/176°F). They are particularly intended to extend the service life of both lubricant and machine parts where unusually high operating and oil reservoir temperatures are encountered.

The high performance characteristics of Tribol 800 are achieved with select polyalkylene glycol (PAG) based synthetic fluids. They feature chemical and thermal stability, high viscosity index, water solubility, and compatibility with metals and elastomers most commonly used in machine construction.

The naturally high resistance to oxidation of the synthetic base fluid is further enhanced by inhibitors. Corrosion protection is very effective even in the presence of water. Also a package of high performance additives act in combination for superior anti-wear and Extreme Pressure (EP) performance.

APPLICATION

The Tribol 800 range are especially suited to reservoirs and circulation systems operating at high temperatures because of heat generated in severe service or high temperatures in the application. Tribol 800 is intended for all types of heavily loaded gears including spur, bevel and worm gears.

Although well suited for all types of gearing and bearings, the Tribol 800 range are particularly effective in controlling wear and reducing friction between sliding surfaces. In addition, they possess a high degree of affinity for cupric metal alloys.

ADVANTAGES

- Shear stability - the synthetic base offers high viscosity index (VI) without the addition of VI improvers. In service, VI improvers can shear, lowering oil viscosity and reducing protection critical for gear sets and bearings. The naturally high VI of Tribol 800 assures full protection for components over a wide range of operating temperatures, speed, and load conditions.
- Long life, extended drain intervals are possible because of the natural aging and oxidation resistance of the synthetic base fluid. Advanced Tribol lubrication technology forms friction-fighting, anti-wear films that can significantly reduce local operating temperatures as gear teeth or bearing surfaces come into contact.
- More protection for components in severe service. The extended EP performance of Tribol 800 offers protection beyond the capabilities of conventional petroleum oils.
- Wear protection under conditions of extreme temperature fluctuation and high loads.
- High efficiency and lower oil temperature, especially in worm gear units.
- High corrosion protection of cast and steel surfaces through special additive packages, even in the presence of water.
- Compatibility with non-ferrous metals through well-formulated synergistic additives.
- Potential energy savings as a result of a lower coefficient of friction.
- Reduction of maintenance costs as a result of significantly increased life of the lubricant.

TYPICAL CHARACTERISTICS

Test	Method	Units	800/100	800/150	800/220	800/320	800/460	800/680	800/1000	800/2200
ISO viscosity group	ASTM D 2422	-	100	150	220	320	460	680	1000	2200
AGMA Lubricant Number	-	-	3EP	4EP	5EP	6EP	7EP	8EP	8AEP	-
Specific gravity @ 60°F	ASTM D 1298	g/cm ³	1.03	1.03	1.04	1.04	1.04	1.05	1.06	1.06
Kinematic Viscosity	ASTM D 445	-	-	-	-	-	-	-	-	-
@ 40°C		mm ² /s	100	150	220	320	460	680	1000	2200
@ 100°C		mm ² /s	20	29	38	59	80	113	157	372
Viscosity Index	ASTM D 2270	-	205	225	225	253	254	271	284	325

Flash Point, COC	ISO 2592/ASTM D92	°C	280	280	290	290	290	290	300	271
Pour Point	ISO 3016/ ASTM D97	°C	-42	-36	-33	-30	-30	-27	-24	-21
Copper Corrosion (3 hrs @ 100°C)	ISO 2160/ ASTM D130	-	1a	1a	1a	1a	1a	1a	1a	1a
Rust Test Procedure A (24 hrs Distilled Water)	ISO 7210/ ASTM D665	-	Pass	Pass	Pass	Pass	Pass	Pass	Pass	Pass
Four Ball Wear Test	-	-	-	-	-	-	-	-	-	-
(40 kg, 75°C/167°F, 1800 rpm, 1 hr) Scar Diameter	-	mm	-	0.35	0.35	0.35	0.35	0.35	0.35	0.34
Four Ball Extreme Pressure Test	ASTM D 2783	-	-	-	-	-	-	-	-	-
Load Wear Index		Kg	35	35	35	35	35	35	35	97
Weld Load		kg	200	200	200	200	200	200	200	315
Four ball wear test Wear scar diameter	DIN 51350-03-B	mm	0.27							
Falex Wear Test, ASTM D 2670, wear teeth	-	-	+2	+2	+2	+2	+2	+2	+2	+2
FZG Test, (A/8.3/90)	DIN 51354	-	>12							
FZG micropitting test	FVA No. 54	-	>10							
Foam Sequence I	ISO 6247 / ASTM D892	mls	0/0							
The viscosity-temperature relationship of these synthetic fluids is not a straight line function on the viscosity-temperature diagram used in Test Methods ASTM D341 and DIN 51536										

Subject to usual manufacturing tolerances.

Additional Information

Tribol 800 synthetic gear oils are water soluble and so spills may be cleaned up with water. They are NOT compatible with mineral (petroleum) based lubricants. Condensation water may be absorbed without the damage of corrosion or a change in viscosity.

Cleaning lubrication systems with a flushing oil or **Tribol 800** prior to the first filling is recommended. To achieve long drain cycles and obtain the economic advantages, systems must be free of contaminants.

The **Tribol 800** range is compatible with most seals including Viton A and nitrile or Buna N (NBR). 800's are NOT compatible with neoprene (polychloroprene) and butadiene seals - mixed polymers, styrenebutadienes, polystyrene, or methacrylates.

Castrol Tribol 800 Series
1/12/2005, Global Version Number 1.0
Tribol 800 Series and the Castrol logo are trademarks of Castrol Limited.

All reasonable care has been taken to ensure that the information contained in this publication is accurate as of the date of printing. However, such information may, nevertheless, be affected by changes in the blend formulation occurring subsequent to the date of printing. Material Safety Data Sheets are available for all Castrol Ltd products. The MSDS must be consulted for appropriate information regarding storage, safe handling and disposal of a product.

Castrol Industrial North America Inc. 150 West Warrenville Road, 605 3E Naperville, IL 60563
Tel: (877) 641 1600 Fax: (877) 648 9801

www.castrol.com/industrial