



## Tribol™ GR 1350-2.5 PD

High performance bearing grease

### Description

Castrol Tribol™ GR 1350-2.5 PD (previously called Optipit™) is a lithium soap based grease with an extremely high viscosity base oil containing the advanced MicroFlux Trans (MFT) additive package.

The Microflux Trans additive technology provides optimum wear protection and an extremely low coefficient of friction even under extremes of pressure, vibration, shock loads, at high or low speeds or varying micro-smoothing of the friction surfaces. Under severe load, components of the MFT additive combination are activated and diffuse into the surfaces, initiating an improvement of their friction characteristics through plastic deformation.

The organic reaction products become a component of the tribopolymer system. Unlike the case with conventional lubricants, the tribopolymers formed by MFT are long-chained compounds with excellent lubricity and adhesion. This means that the load carrying area is improved and that a hydrodynamic lubrication film is easier to maintain. This unique physio-chemical reaction achieves a non-sacrificial micro-smoothing of the friction surfaces.

### Application

Tribol GR 1350-2.5 PD is especially suited for rolling and sliding bearings in dusty and humid environments. It builds a stable grease collar at the bearing edges, supporting the seals to prevent penetration of dirt, water and other contaminations. Tribol GR 1350-2.5 PD enables a hydrodynamic lubricating film even at low speeds.

Developed for the lubrication of anti-friction and plain bearings running at low speeds which require extremely high oil viscosity, or operate in wet and dusty atmospheres found in applications such as:

- Mining, especially open-pit mining
- The steel industry/tube mills under heavy shock loads and vibration
- Equipment exposed to sea water, in harbours, and on ships and drilling platforms
- Yaw gear on wind turbines

### Advantages

- Water and dirt repellent – the grease is still effective in adverse environments
- High load bearing capacity - enables the extension of operating periods even under high loads whilst still maintaining optimum wear protection.
- Establishes a protective layer of MFT – this additive system can effectively increase the load bearing area, therefore reducing unit pressures, operating temperatures and wear which can increase service life of both parts and lubricant
- Improved bearing surfaces for longer service life result from the 'running in' effect of MFT
- Extremely low coefficients of friction – energy savings and reduced noise levels
- Good adhesion due to high oil viscosity – the film coating stays on the surface
- Reduction of running-in period

## Typical Characteristics

| Name  | Method               | Units                                      | Tribol GR 1350-2.5 PD |
|---|----------------------|--|-----------------------|
| Appearance  | Visual               | -  | Brown                 |
| Thickener type  | -                    | -  | Lithium               |
| Base Oil  | -                    | -  | Mineral oil           |
| Consistency   | ISO 2137/ASTM D217   | NLGI grade                                 | 2.5                   |
| Density @ 20 °C/68 °F   | IP 530               | kg/m <sup>3</sup>                          | 905                   |
| Worked Penetration (60 strokes @ 25 °C/77 °F)                               | ISO 2137/ASTM D217   | 0.1 mm                                     | 245 - 275             |
| Worked Penetration (100,000 strokes @ 25 °C/77 °F) - change from 60 strokes | ISO 2137/ASTM D217   | 0.1 mm                                     | max. 25               |
| Dropping point  | ISO 2176/ASTM D566   | °C/°F                                      | max. 250/max. 482     |
| Base Oil Viscosity @ 40 °C/104 °F   | ISO 3104/ASTM D445   | mm <sup>2</sup> /s                         | 1350                  |
| Rust Test - EMCOR (distilled water)   | ISO 11007/ASTM D6138 | Rating                                     | max. 1/1              |
| Copper Corrosion (24 hrs, 100 °C/212 °F)                                    | ASTM D4048           | Rating                                     | max. 1b               |
| SRV Friction and Wear test - 5ae  | ASTM D5707           | coeff. of friction/wear scar diameter (mm) | 0.082/0.53            |
| Oil Separation (168 hrs @ 40 °C/104 °F)                                     | IP 121/DIN 51817     | %wt  | 0.3                   |
| Flow pressure @ -20 °C/-4 °F  | DIN 51805            | hPa  | 950 - 1350            |
| Water Resistance @ 90 °C  | DIN 51807-1          | Rating                                     | 1                     |

Subject to usual manufacturing tolerances.

## Additional Information

In order to minimise potential incompatibilities when converting to a new grease, all previous lubricant should be removed as much as possible prior to operation. During initial operation, relubrication intervals should be monitored closely to ensure all previous lubricant is purged.

**This product was previously called Optipit. The name was changed in 2015.**

Tribol™ GR 1350-2.5 PD

20 May 2015

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Industrial, North America Inc., 150 West Warrenville Road, 603 1E Naperville, IL 60563

Tel: (877) 641 1600 Fax: (877) 648 9801

[www.castrol.com/industrial](http://www.castrol.com/industrial)