

Castrol Brayco 785

Gas Turbine Preservative and Break-in Oil

Description

Castrol Brayco™ 785 is a petroleum-based preservative and break-in oil that can be used to protect gas turbines during shipping, storage, and prolonged shut-down periods.

Application

Brayco 785 was developed with the cooperation of a major manufacturer of gas turbine engines. While this product may also be used as a break-in oil, it is not meant for regular service as a gas turbine lubricant, and should be drained out and replaced by a manufacturer approved product when the engine is placed back on line. By using Brayco 785 in the test cell on new and overhauled engines, all that is necessary for internal preservation is to remove the test instrumentation (lines, etc.). Additionally, fogging a MIL-PRF-23411 / MIL-PRF-81309 fluid into the inlet on cold-crank will prepare the engine for shipping. A treated engine is typically preserved for at least two years.

Typical Characteristics

Test	Method	Units	Result
Gravity API @16°C/60°F	ASTM D287	degrees	31.5
Specific Gravity @16°C/60°F	ASTM D287		0.87
Density @16°C/60°F	ASTM D287	Lbs/gal	7.2
Flash Point, COC	ASTM D92	°C/°F	225/437
Fire Point, COC	ASTM D92	°C/°F	250/482
Viscosity @100°C/210°F @40°C/100°F	ASTM D445	cSt	5.95 38.5
Viscosity Index	ASTM D2270		107
Pour Point	ASTM D97	°C/°F	9.5
Total Acid Number	ASTM D664	mg KOH/gm	1.9
Four Ball Wear, 40kg, 1 hr., 1200 rpm @75°C/167°F	ASTM D2266	mm	0.42
Foam Sequence 1 Sequence 2 Sequence 3	ASTM D892 (Alt.)	ml	0/0 0/0 0/0
Humidity Cabinet: 3 test panels	ASTM D1748		720 hours

Subject to usual manufacturing tolerances.

Additional Information

Specification

Brayco 785 meets Solar Turbines ES9-248-1A

Shelf Life

Brayco 785 has a maximum recommended shelf life of 9 years from date of manufacture. This shelf life assumes that the product is stored in its original unopened packaging in ambient temperature conditions.

Castrol, Brayco, and the Castrol logo are trademarks of Castrol Limited, used under license

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet.

It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Industrial North America Inc. 150 West Warrenville Road, 605 3E Naperville, IL 60563
Tel: (877) 641 1600 Fax: (877) 648 9801

www.castrol.com/industrial

Castrol Brayco 785

Page 2 / 2

16 July 2009, Version 1