



## Castrol Brayco Micronic 889

Coolant Fluid, Hydrolytically Stable  
Dielectric

### Description

Castrol Brayco™ Micronic 889 is a clear and bright, synthesized hydrocarbon based, heat transfer fluid and dielectric coolant

### Application

Brayco Micronic 889 is designed for use in electrical/electronic cooling of ground based and airborne closed loop systems. It offers high specific heat in comparison to other hydrocarbons, esters and silicone fluids. This product also provides the superior oxidative stability, low temperature properties and the hydrolytic stability characteristics typical of polyalphaolefin products. Brayco Micronic 889 has excellent dielectric properties and is harmless to most common metals of construction. It is compatible with (low acrylonitrile) BUNA N compounds and fluoroelastomers such as Viton.

## Typical Characteristics

TEST (ASTM)	DESCRIPTION	MIL-PRF-87252C REQUIREMENT	RESULT
D 287	Specific Gravity, 16/16°C (60/60°F), g/ml		0.85
Table 8	Pounds per Gallon		7.1
D 445	Kinematic Viscosity, cSt @ 100°C (212°F) @ 40°C (104°F) @ -40°C (-40°F) @ -54°C (-65°F)	1.65 Minimum 5.1 Minimum 300 Maximum 1300 Maximum	1.7 5.1 250 800
D 92	Flash Point, COC, °C (°F)	150 Minimum	166 (331)
D 92	Fire Point, COC, °C (°F)	160 Minimum	180 (356)
D 1744	Water Content, KFR, ppm Saturation Point, ppm	50 Maximum	32 200
D 664	Total Acid Number (TAN), mgKOH/gm	0.20 Maximum	0.1
D 877	Dielectric Strength, KV	35 Minimum	35
D 1169	Volume Resistivity 25°C (77°F), ohm-cm 135°C (275°F), ohm-cm	1.0 × 10 <sup>10</sup> Minimum Report	1.5 × 10 <sup>14</sup> 8.0 × 10 <sup>12</sup>
Spec/Auto Counter	Solid Particle Contamination Autocount, per 100 ml 5 - 15 microns 16 - 25 microns 26 - 50 microns 51 - 100 microns 100+ microns	10,000 Maximum 1,000 Maximum 150 Maximum 20 Maximum 5 Maximum	2000 128 48 4 0
D 4636	Corrosion and Oxidation Stability 121°C (250°F), 168 hrs Copper Corrosion, ASTM D 130 Copper, weight loss, mg/cm <sup>2</sup> Steel, weight loss, mg/cm <sup>2</sup> Aluminum, weight loss, mg/cm <sup>2</sup> Magnesium, weight loss, mg/cm <sup>2</sup> Cadmium, weight loss, mg/cm <sup>2</sup>	3A Maximum 0.4 Maximum 0.2 Maximum 0.2 Maximum 0.2 Maximum 0.2 Maximum	2B 0.03 0.04 0.06 0.04 0.07
D 4636	Rubber Swell, Chloroprene (AMS 3217/3) 70°C (158°F), 168 hrs, %	0-10	7.8
D 287	Density, g/ml @ 0°C (32°F) @ 20°C (68°F) @ 40°C (104°F) @ 100°C (212°F) @ 160°C (320°F)		0.811 0.794 0.777 0.723 0.661

TEST (ASTM)	DESCRIPTION	RESULT
D 2766	Specific Heat, cal/g, °C @ -18°C (0°F) @ 10°C (50°F) @ 38°C (100°F) @ 93°C (200°F)	0.49 0.52 0.54 0.58
D 1903	Coefficient of Thermal Expansion, per °C 0 - 50°C 50 - 100°C 100 - 150°C 150 - 190°C	$8.3 \times 10^{-4}$ $9.2 \times 10^{-4}$ $10.3 \times 10^{-4}$ $11.7 \times 10^{-4}$
D 2155	Auto Ignition Temperature	324°C (615°F)
D 877	Dielectric Constant, 25°C (77°F), KHz Vapor Pressure, Isotemiscopes, mm Hg 65.5°C (150°F) 93.3°C (200°F) 121°C (250°F) 149°C (300°F) 177°C (350°F) 204°C (400°F) 232°C (450°F) 260°C (500°F)	2.1 0.3 1.2 4 11.5 32 73 148 300
D 3114	Thermal Conductivity, BTU/hr, Ft <sup>2</sup> (°F/Ft) 0°C (0°F) 10°C (50°F) 24°C (75°F) 38°C (100°F) 93°C (200°F) 149°C (300°F) 204°C (400°F) 260°C (500°F)	0.085 0.083 0.082 0.082 0.078 0.075 0.072 0.069
Spec	Viscosity Index	112
Spec	Pour Point, °C (°F)	<-65 (<-85)

Subject to usual manufacturing tolerances.

## Additional Information

### Temperature Range

Brayco Micronic 889 is designed to operate over the temperature range of -54°C to 135°C (-65°F to 275°F)

### Specification

Brayco Micronic 889 is qualified to and meets the requirements of MIL-PRF-87252C. This fluid is identified by NATO Code Number S-1748.

Castrol, Brayco, and the Castrol logo are trademarks of Castrol Limited, used under license

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet.

It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Industrial North America Inc. 150 West Warrenville Road, 605 3E Naperville, IL 60563  
Tel: (877) 641 1600 Fax: (877) 648 9801

[www.castrol.com/industrial](http://www.castrol.com/industrial)

Castrol Brayco Micronic 889